

## Grease Fluor H

### Extremely high temperature grease

#### Description

Grease Fluor H is a white, homogeneous, butter-like perfluorinated polyether grease. Particularly resistant to oxygen, chemical agents and high temperatures. Grease Fluor H can be used in contact with hot and cold water, vapour, fuel, acids, alkaline products, non-fluorinated solvents and chlorinated solvents. Continuous operating temperature of 250 °C. Can reach 280 °C peak temperature in short period.

#### Applications

Grease Fluor H provides exceptional stability to heat and chemical agents and shows high efficiency in:

- Electric motors bearings
- Roller bearings in furnace wagon wheels
- Thermal stabilized ball bearings in clip chains
- Chain bearings in drying plants
- Stenter chains bearings
- Vacuum pump units
- Handling and pumping of alkaline products and acids

- Handling and pumping of petroleum, fuel oils and oils
- Handling and pumping of solvents
- Oven lubrication
- Stabilisation or polymerisation in glass production
- Textile & plastic film production
- Nuclear sites
- Production of corrugated
- Glass house construction

As stated herein Grease Fluor H is insoluble in most of the solvents, this is why such solvents are not suitable for the cleaning of mechanisms and tools used in contact with the product. To remove or dissolve only fluorinated cleaners will be effective. Fluorsol X or Fluorsol XL can be used.

#### Cautions

In tests Grease Fluor H shows very low ingestion and skin toxicity, therefore it is not dangerous for operators. Should only be applied onto perfectly clean parts, free of any type of contamination or protection such as oil, grease, anti-rust protectors and dust.


#### Compatibility

Synthetic materials and elastomers compatibility:

Material	Compatible yes/no
Cellulose acetate	Yes
Polyacetal resin	Yes
Polyamides	Yes
Polyethylene	Yes
Polycarbonates	Yes
Polyurethanes	Yes
Polytetrafluorethylene	Yes
Ethyl-propyl-terpolimer rubber	Yes
Butadiene-acrylonitrile rubber	Yes

All performance data on this Technical Data Sheet are indicative only and can vary during production

**Matrix Specialty Lubricants BV - [info@lubes-portal.com](mailto:info@lubes-portal.com) - [www.lubes-portal.com](http://www.lubes-portal.com)**



## Typical performance data

	Test method	H 0	H 1	H 2
Colour		White		
Thickener, soap type		PTFE		
Base oil nature		Fluorinated polyether		
Base oil viscosity @ 40 °C, cSt	ASTM D445	500	500	500
NLGI consistency		0	1	2
Penetration @ 25 °C, x 0,1 mm	ASTM D217	355-385	310-340	265-295
Drop point °C	DIN 51801	None	None	None
Specific gravity @ 25 °C		1,93	1,93	1,92
Evaporation loss, %	ASTM D972			
• Weight loss 22 hr/65 °C		0	0	0
• Weight loss 22 hr/150 °C		0	0	0
• Weight loss 22 hr/200 °C		1	1	1
• Weight loss 22 hr/250 °C		4	4	4
Oil separation, %	FTMS 791.321			
• After 30 hr/65 °C		0	0	0
• After 30 hr/100 °C		3,5	3,5	3,5
• After 30 hr/200 °C		12	12	12
Oxidation stability @ 100 °C, bar	ASTM D942	0	0	0
Water resistance @ 90 °C	DIN 518079	0	0	0
4-balls wear test, weld load, kg	IP 239	>400	>400	>400
Specific resistance (ohm x cm)		$4 \times 10^{14}$	$4 \times 10^{14}$	$4 \times 10^{14}$
Max speed factor (n x mm)		300.000	300.000	300.000
Service temperatures, °C		-30 – 250	-30 – 250	-25 – 250
Peak temperatures, °C		280	280	280

All performance data on this Technical Data Sheet are indicative only and can vary during production  
**Matrix Specialty Lubricants BV - [info@lubes-portal.com](mailto:info@lubes-portal.com) – [www.lubes-portal.com](http://www.lubes-portal.com)**